# Aluminium Alloy DTD5014A T6 Bar



## **SPECIFICATIONS**

Commercial	2618A	
------------	-------	--

Aluminium alloy DTD5014A – 2618A is a high strength alloy available mainly in the form of extruded bar and also extruded sections. Note that the standard specifying DTD5014A has been cancelled.

#### CHEMICAL COMPOSITION

Element	% Present	
Copper (Cu)	1.8 - 2.7	
Magnesium (Mg)	1.2 - 1.8	
Lithium (Li)	1.2 - 1.8	
Iron (Fe)	0.9 - 1.4	
Nickel (Ni)	0.8 - 1.4	
Manganese (Mn)	0.25 max	
Silicon (Si)	0.15 - 0.25	
Titanium + Zirconium (Ti+Zr)	0.25 max	
Titanium (Ti)	0.2 max	
Zinc (Zn)	0.15 max	
Others (Total)	0.15 max	
Other (Each)	0.05 max	
Aluminium (Al)	Balance	

## **ALLOY DESIGNATIONS**

Aluminium alloy DTD5014A has similarities to the following standard designations and specifications: 2618A 2618

### TEMPER TYPES

The most common temper for DTD5014A – 2618A aluminium is T6

• T6 - Solution heat treated and artificially aged

#### SUPPLIED FORMS

Solution heat-treated and water quenched Precipitation heat-treated and air cooled

- Bar
- Extrusions

## MECHANICAL PROPERTIES

Diameter (mm)	Proof Strength	Tensile Strength	Elongation
Up to & incl. 10	320 Min	400 Min	5% Min
Over 10 up to & incl. 100	340 Min	420 Min	7% Min

#### CONTACT

Address:

Gould Alloys Ltd
Markham Lane
Markham Vale
Chesterfield
S44 5HS
United Kingdom

Tel: +44 (0) 1246 263300

Email: sales@gouldalloys.co.uk
Web: www.gouldalloys.co.uk

## **REVISION HISTORY**

Datasheet Updated 23 March 2022

## **DISCLAIMER**

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.