

## SPECIFICATIONS

Commercial	2014A - Obsolete
------------	------------------

### Applications:

High strength structural components: aircraft (e.g. fittings and wheels), military vehicles and bridges, forgings for trucks and machinery (hydraulic etc.). Weapons manufacture, structural applications.

### Characteristics:

Heat treatable alloy. High mechanical strength slightly higher than 2011 and 2017A.

## CHEMICAL COMPOSITION

BS L103(1971)  
Alloy L103

Element	% Present
Copper (Cu)	3.9 - 5
Manganese (Mn)	0.4 - 1.2
Silicon (Si)	0.5 - 0.9
Magnesium (Mg)	0.2 - 0.8
Iron (Fe)	0.5 max
Titanium + Zirconium (Ti+Zr)	0.2 max
Zinc (Zn)	0.2 max
Nickel (Ni)	0.2 max
Chromium (Cr)	0.1 max
Tin (Sn)	0.05 max
Lead (Pb)	0.05 max
Aluminium (Al)	Balance

Forging stock shall be supplied non heat treated.

Forgings shall be supplied solution treated and aged at room temperature.

Heat treatment shall be as follows:

1. Solution treat by heating at a temperature of 500 +/- 5C and quenching in water at a temperature not less than 40C nor more than 70C.
2. Age at room temperature for not less than 48 hours.

## ALLOY DESIGNATIONS

Aluminium alloy L103 - 2014A is covered by Standard BS EN 2100 and has similarities to the following standard designations and specifications **but may not be a direct equivalent:**

2014 / 2014A      AMS 4121

## TEMPER TYPES

The most common temper for L103 - 2014A aluminium forging stock is T4

- T4 - Solution heat treated and naturally aged to a substantially stable condition
- T6 - Solution heat treated and artificially aged

## SUPPLIED FORMS

L103-2014A aluminium is supplied as forging stock and forgings made from cast billet, extruded sections or rolled plate

- Forgings
- Bar
- Castings
- Extrusions
- Plate

## GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.8 g/cm <sup>3</sup>
Melting Point	640 °C
Thermal Expansion	22.8 x10 <sup>-6</sup> /K
Modulus of Elasticity	73 GPa
Thermal Conductivity	134 - 135 W/m.K

## MECHANICAL PROPERTIES

BS L103(1971)	
Property	Value
Hardness Brinell	104 HB
Tensile Strength	370 N/mm <sup>2</sup>
Elongation A	14 %
0.2% Proof Stress	225 N/mm <sup>2</sup>

The values shown in the mechanical properties table apply to a test sample prepared by forging representing extruded forging stock and forgings made from cast billets, hot rolled plate and extruded stock. The specification contains other properties for test samples prepared by machining representing extruded forging stock and forgings made from extruded stock.

The hardness values apply to forgings and forged test pieces.

## CONTACT

Address:	Gould Alloys Ltd Markham Lane Markham Vale Chesterfield S44 5HS United Kingdom
Tel:	+44 (0) 1246 263300
Email:	<a href="mailto:sales@gouldalloys.co.uk">sales@gouldalloys.co.uk</a>
Web:	<a href="http://www.gouldalloys.co.uk">www.gouldalloys.co.uk</a>

## REVISION HISTORY

Datasheet Updated	09 January 2014
-------------------	-----------------

## DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.