

#### **SPECIFICATIONS**

Commercial	2014A
Commercial	20147

Aluminium alloy L157 – 2014A is a high strength sheet and strip specification.

The standard specifying this grade has been superseded by BSEN 2395

# CHEMICAL COMPOSITION

BS L157(1978) Alloy L157				
Element	% Present			
Copper (Cu)	3.9 - 5			
Manganese (Mn)	0.4 - 1.2			
Silicon (Si)	0.5 - 0.9			
Magnesium (Mg)	0.2 - 0.8			
Iron (Fe)	0.5 max			
Zinc (Zn)	0.25 max			
Titanium + Zirconium (Ti+Zr)	0.2 max			
Titanium (Ti)	0.15 max			
Others (Total)	0.15 max			
Chromium (Cr)	0.1 max			
Nickel (Ni)	0.1 max			
Other (Each)	0.05 max			
Aluminium (Al)	Balance			

# ALLOY DESIGNATIONS

Aluminium alloy L157 has similarities to the following standard designations and specifications: 2014A

## TEMPER TYPES

The most common temper for L157 aluminium is: • T6 - Solution heat treated and artificially aged

# SUPPLIED FORMS

L157 aluminium is supplied as Clad Sheet and Strip.

- Sheet
- Strip

## GENERIC PHYSICAL PROPERTIES

Property	Value	
Density	2.80 g/cm <sup>3</sup>	
Melting Point	640 °C	
Thermal Expansion	22.8 x10 <sup>-6</sup> /K	
Modulus of Elasticity	73 GPa	
Thermal Conductivity	155 W/m.K	
Electrical Resistivity	40 % IACS	

#### MECHANICAL PROPERTIES

Thickness (mm)	Proof Strength (Min)	Tensile Strength (Min)	Elongation % (Min)
Over 0.4 up to & incl. 0.8	370	430	6
Over 0.8 up to & incl.1.6	380	440	7
Over 1.6 up to & incl. 6.0	390	440	7



#### CONTACT

Address:	Gould Alloys Ltd Markham Lane Markham Vale Chesterfield S44 5HS United Kingdom	
Tel:	+44 (0) 1246 263300	
Email:	sales@gouldalloys.co.uk	
Web:	www.gouldalloys.co.uk	

#### **REVISION HISTORY**

Datasheet Updated 07 January 2014

#### DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.