

Aluminium Alloy

L61 'O' Sheet



SPECIFICATIONS

Commercial	3103
------------	------

Applications:

Equipment for heating and cooling: heat exchangers, air condition evaporators, motor vehicle radiators, freezer linings, office equipment. Tubing, piping, containers, closures. Cladding alloy. Pressure vessels, aircraft and military components.

Characteristic Properties:

Very good resistance to atmospheric corrosion. Very good weldability. Good formability by pressing, drawing and roll forming. Medium strength alloy. Better mechanical properties (in particular at elevated temperatures) than 1xxx-alloys. Properties very close to those of 3003.

Precautions and Warnings:

Actual performance requires careful design of tools, lubrication and metal surface condition.

CHEMICAL COMPOSITION

BS 4L61(1985)
Alloy L61

Element	% Present
Manganese (Mn)	0.9 - 1.5
Iron (Fe)	0.7 max
Silicon (Si)	0.5 max
Magnesium (Mg)	0.3 max
Zinc (Zn)	0.2 max
Others (Total)	0.15 max
Copper (Cu)	0.1 max
Chromium (Cr)	0.1 max
Titanium + Zirconium (Ti+Zr)	0.1 max
Other (Each)	0.05 max
Aluminium (Al)	Balance

The material shall be supplied annealed (O).

ALLOY DESIGNATIONS

Aluminium alloy L61 - 3103 is covered by standard BS EN 4L61 (1985)

TEMPER TYPES

The most common tempers for L61 - 3103 aluminium is:

- O - Soft

SUPPLIED FORMS

L61 - 3103 aluminium is supplied in the following forms:

- Sheet
- Strip

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.73 g/cm ³
Melting Point	655 °C
Thermal Expansion	23.1 x10 ⁻⁶ /K
Modulus of Elasticity	69.5 GPa
Thermal Conductivity	160 W/m.K
Electrical Resistivity	42 % IACS

MECHANICAL PROPERTIES

BS 4L61(1985)
Sheet
0.4mm to 0.8mm

Property	Value
Elongation A50 mm	20 Min %
Tensile Strength	90 Min - 130 Max N/mm ²

Mechanical properties relate to material with a nominal thickness of 0.4mm up to and including 0.8mm. The specification contains other values for different material thicknesses.

CONTACT

Address:	Gould Alloys Ltd Markham Lane Markham Vale Chesterfield S44 5HS United Kingdom
Tel:	+44 (0) 1246 263300
Email:	sales@gouldalloys.co.uk
Web:	www.gouldalloys.co.uk

REVISION HISTORY

Datasheet Updated	09 January 2014
-------------------	-----------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.